

MasterSeal[®] M 800 (formerly known as Conipur M 800)

Spray applied elastomeric polymer waterproofing membrane

DESCRIPTION

MasterSeal M 800 is a solvent free, two component waterproofing membrane. Due to its fast cure speed it can only be applied by special, two component spray equipment.

RECOMMENDED USES

MasterSeal M 800 is intended for use in general waterproofing applications such as car park decks, podium decks and cut and cover tunneling.

Using the appropriate primer, **MasterSeal M 800** can be applied to most substrates including concrete, galvanised steel, aluminium, UPVC, glass reinforced polyester etc.

FEATURES AND BENEFITS

- **Fast reacting spray application** – Complex details both horizontal and vertical easy to waterproof
- **Application to vertical surface without runs** – Installation to walls not problem
- **Monolithic** – No laps, welds or seams
- **Fully bonded** – Moves with the structure
- **High water vapour permeability** – Low risk of blistering in service
- **Crack bridging capability**- Can cope with cracks that occur after installation
- **Solvent and monomeric isocyanate free** – Increased safety for applicators
- **Unaffected by standing water or ground water** – Suitable for constant water contact
- **Thermoset** – Does not soften at elevated temperatures encountered on a roof
- **Remains elastic at low temperatures-Tg approx. -45°C** – Suitable for all Asia Pacific climates

PROPERTIES

Mixing ratio A:B	
by weight	100 : 73
by volume	100 : 70
Density @ 23°C	Part A 1.04 kg/L Part B 1.10 kg/L

Viscosity @ 23°C	Part A Part B	>1500mPas >1400mPas
Gel time (hand mixed) @ 23°C		18 seconds
Ambient temperature range		5 °C to 40 °C
Substrate temperature range		5 °C to 60 °C
Relative humidity		max. 85 %

Technical data cured material (sprayed film except where stated)

Shore A hardness	14 Days	75-80
Tensile strength	DIN 53504	>8 MPa
Elongation	DIN 53504	420 +/- 100%
Tear strength	DIN 53515	16 N/mm

The performance data is typical and based upon controlled laboratory conditions. Actual performance on the job site may vary from these values based on actual site conditions.

APPLICATION

Surface Preparation

The concrete substrates to be coated must be at least 14 days old, dry and load-bearing, free of laitance as well as substances which impair adhesion such as oil, grease, rubber skid marks, paint or other contaminants. Preparation of the substrate by grit or shot blasting, high-pressure water jetting, grinding or scarifying is necessary for plain concrete or when the primer has become soiled or when the re-coating interval has been exceeded. Prior to application of the primer the bond strength of the substrate must be at least 1.5 MPa (check with an approved pull-off tester ie "Proceq", load rate 100 N/sor others as approved by BASF).

The substrate to be coated must be protected against rising damp by having a damp proof membrane installed if it is a slab in contact with the ground.

MasterSeal M 800 can only be applied by means of a suitable heated two component spray machine. For optimum results the material should be heated to 60-70°C. For advice on machines, please contact your local BASF technical representative.



The Chemical Company

MasterSeal® M 800 (formerly known as Conipur M 800)

MasterSeal M 800 when sprayed results in a uniform grey colour which gives the sprayer a visual control of the quality of the mixing as machine faults become immediately obvious. This can reduce costly clean up time and material wastage. Due to the fast reaction it is possible to rapidly build thicknesses from 1.0 to > 6 mm.

Surrounding areas should be protected from overspray by masking off with e.g. polyethylene sheet, or paper. Care should be taken to prevent spray mist being carried by wind by erecting suitable barriers. The temperature of the substrate should be min. 3°C above the dew point prior to application of the membrane.

Primer

Primer has to be cured to a 'tack-free' state prior to the application of **MasterSeal M 800**. Use the following guide to select the appropriate primer:

Substrate	Primer
Concrete	MasterEmaco 2525 MasterTop P1601 MasterTop P1602 MasterTop P 660
Other substrates	Contact your local BASF Construction Chemicals technical representative

Top Coats and Wear Coats

MasterSeal M 800 does not have sufficient UV and weather resistance to be used in exposed applications without protection. A number of top coats and wear coats are available including **MasterSeal TC 258** which can be broadcast with dry silica sand to provide a hard wearing, non-slip surface.

Note: if rain falls or dew occurs on the surface of **MasterSeal M 800** then the membrane must be dried and MasterTop 691 applied prior to the application of any wear coat or two part top coat (even if the re-coat interval has not been exceeded). In the tropics any exposed **MasterSeal M 800** must be treated as above if left overnight.

For more information about application, please obtain a copy of the BASF "Application Guide for MasterSeal Spray Membrane System" from your local representative.

ESTIMATING DATA

MasterSeal M 800 is normally applied at 1.8 – 2.4 kg/m². This corresponds to a thickness of approx. 1.6 – 2.2mm.

PACKAGING

MasterSeal M 800 is supplied in 200kg drums – Part A and 200kg drums – Part B.

SHELF LIFE

Twelve months if stored in original containers under dry conditions at a temperature between 10-30° C. Do not store in direct sunlight for more than 3 days.

PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Material Safety Data Sheet (MSDS) from our office or our website.

® = registered trademark of BASF group in many countries

ID#MasterSeal_M800 asean v1.5 1013

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF Construction Chemicals publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF Construction Chemicals, are responsible for carrying out procedures appropriate to a specific application.

BASF Construction Chemicals offices in ASEAN

Singapore	Malaysia	Indonesia	Thailand	Vietnam	Philippines	Hong Kong
Tel: +65-6861-6766	Tel: +60-3-5628-3888	Tel: +62-21-2988-6000	Tel: +66-2769 8564	Tel: +84-650-374-3100	Tel: +63-2-811-8000	Tel: +852-2408-4400
Fax: +65-6861-3186	Fax: +60-3-5628-3776	Fax: +62-21-2988-5935	Fax: +66-2769-8584	Fax: +84-650-374-3200	Fax: +63-2-838-1025	Fax: +852-2408-4401

Website: www.master-builders-solutions.asia-pacific.basf.com